



## SUPERSETA

Satin synthetic enamel for indoor/outdoor



### technical data sheet

Revision 1 fro 01/02/2017

<b>Converter name</b>	<b>PS250</b>
<b>Destination</b>	Protective and decorative finish for different types of surfaces (metal, wood, indoor walls) as well as properly prepared. Suitable for the exposure of atmospheric effects, in marine and light industrial environments.
<b>Characteristics</b>	<p>Excellent filling</p> <p>Excellent covering</p> <p>Ease of recovery</p> <p>Good gloss and color retention</p> <p>Excellent resistance to sagging</p>
<b>VOC (Directive 2004/42/CE) ( g/l )</b>	Monocomponent paintings at high performances. EU limit value for this product (Cat. A/i): 500 g/l (2010). This product contains max. <500 g/l
<b>Recommended surface and temperature conditions</b>	<p>Avoid applications at room temperature under +5°C or over +35°C and relative room humidity over 80%. Verify surface suitability according to humidity degree with hygrometer . Support temp: min: +5°C - max +35°C.</p> <p>WARNING: areate the environment to avoid humidity accumulation</p> <p>WARNING: the complete film polymerisation comes after 7-10 days at T=20°C e U.R.60%</p> <p>Avoid applications with superficial condensation or under direct sun action</p> <p>In enclosed spaces, properly ventilate the area during appliacion and drying</p>
<b>Reccomendations</b>	<p>Well mix before use.</p> <p>We reccomend to apply the product evenly along the whole painting surface, avoiding to leave uncovered parts from which it could start a deterioration process of the applied cycle film and the support.</p> <p>At application temperatures lower than +15°C it could be necessary to add more solvent to obtain teh desired application viscosity, Too much thinner will lead to a diminution of the sagging resistsance and could bring to defects during the application.</p> <p>High humidity can cause opacification dulling during the application.</p> <p>We recommend the use of soft sponges with neutral detergent to clean the painted surfaces. Avoid using abrasive cloths or rags as well as alcool detergents or any type of solvent.</p> <p>WARNING: for indoor application areate the environment and wear the adequate individual protection instruments</p> <p>The antirust-painted surfaces must be recoated as soon as possible with finish enamels , in order too keep unchanged over time the anticorrosive power of their pigments, which could be considerably reduced for long periods outdoor</p>

## SUPERSETA

Satin synthetic enamel for indoor/outdoor



### Application cycle

#### Never painted ferrous metal surfaces

Completely remove the possible calamine and rust on the surface through sandblasting Sa 2 1/2 or manual or mechanical cleaning (brushing ST3)

WARNING: the sanded surfaces must be recovered with antirust first coat in 8 hours

Carefully wash to eliminate possible contamination substances

Be sure that the support is completely dry

Apply an anticorrosive first coat as our PROTECTOR 7000 or ZINCPALST 11254 or 241 GLICEROFTALICO

After at least 12 hours apply 2 coats of SUPERSETA with an interval of at least 24 hours from each other

#### Already painted ferrous metal surfaces

Cleaning through manual or mechanical system until complete elimination of old painting coats which are not well anchored and of possible rust spots.

Roughen the old, well anchored paintings and eliminate the sanding dust.

In case of strongly deteriorated surfaces we recommend to eliminate the old paintings and the rust caused by sand blasting Sa 2 1/2 or to remove paint and then eliminate the rust through cleaning by manual or mechanical system (brushing ST3).

WARNING: the sanded surfaces must be covered with a first antirust coat in 8 hours

Remove the dust from the surface

Be sure that the support is completely dry.

Apply 1 coat of anticorrosion first coat as our line PROTECTOR 7000 or ZINCPALST 11254 or 241 GLICEROFTALICO

After at least 12 hours apply 2 coats of SUPERSETA with an interval of at least 24 hours from each other

#### Galvanized surfaces, aluminum and light alloys

Carefully clean the surface from possible oxides through manual or mechanical system cleaning

Otherwise, carefully clean with solution DECAPHOS and let it work for a few minutes before a careful washing for the complete removal of the phosphatizing and degreasing solution

WARNING: residual of the solution DECAPHOS on the surface can compromise the good success of the painting cycle Be sure that the support is perfectly dry

Apply 1 coat of anticorrosive primer as our ZINCPALST 11254

After at least 12 hours apply 2 coats of SUPERSETA with an interval of at least 24 hours from each other

#### PVC and ABS surfaces

Remove dust from support.

Check that the support is perfectly dry.

Apply a coat of anticorrosive primer like our ZINCPALST 11254 .

After at least 12 hours apply two coats of Nome Prodotto with a 24 hours interval from each other.

## SUPERSETA

Satin synthetic enamel for indoor/outdoor



### technical data sheet

Revision 1 fro 01/02/2017

#### Application cvcle

##### New or carried forward wood surfaces

Lightly sand to remove the raised wood fibers. Remove the possible resin through adequate thinner. Fill the imperfections with synthetic stucco. sand the stuccoed parts and remove dust. Be sure that the wall is not too much wet. On high absorption woods apply a coat of 1540 LIGNOWAX to uniform the surface absorptions.

BE CAREFUL to the treatment on tannin rich woods. In order to reduce the dark spots formation, apply adequate insulating first coat

Sand the surface and then apply 1 or 2 first coat of filling first coat as our D'ECO' UNIVERSAL PRIMER or DUROPAC. After at least 12 hours apply 2 layers of SUPERSETA with an interval of at least 24 hours from each other. .

##### Painted wood surfaces

Sand to eliminate the wood fibers

Remove old paintings not well anchored.

Roughen the old well anchored painitings and eliminate the sanding dust

Remove the possible resin by using adequate thinner

Plaster imperfections with synthetic stucco. Sand the stuccoed parts and remove dust

Make sure that the wood isn't too much wet.

Apply 1 or 2 coats of filling primer as D'ECO UNIVERSAL PRIMER or DUROPAC

After at least 12 hours apply 2 coats of SUPERSETA with at least 24 hours interval from each other

#### Characteristics and technical informations

Data observable at T=20°C and 60% relative humidity

#### Tin aspect RESIN Color

Liquid. Light thixotropic.

Synthetic

Transparent and neutral

Paints achievable with MCS tintometric system

The brilliance can change depending on the paint

#### Use



Airbrush



Brush



Roll





# SUPERSETA

Satin synthetic enamel for indoor/outdoor



## technical data sheet

Revision 1 fro 01/02/2017

**Thinner** Ecoselva or CS/3000

**Tools' cleaning** CS/3000

### Application process

#### Air Spray

Thinner (% Volume)	CS/3000	5 - 10
Noozle diameter	0,9 - 1,2	
Noozle pressure (Atm/Mpa)	3 - 4	

#### BRUSH / ROLLER

Thinner (% Volume)	CS/3000	0 - 5
--------------------	---------	-------

### TECHNICAL DATA

Mass density ( kg/l )	1,23	
Solids content by vol. ( % )	58	
Solids content by weight ( % )	70	
Brookfield viscosity (cP)	-	
ASTM 4 cup viscosity ( s )	-	
Brilliance ( % )	20 - 30	Satin
Out of dust (minutes )	2	
Touch dry ( h )	3	
Depth dry ( days )	5	
recommended dry film thickness (dtf) ( $\mu\text{m}$ )	30 - 40	
Theoretical spreading rate ( $\text{mq}^2/\text{lt}$ )	19 - 14	
Complete polymerisation - days	7 - 10	
Recoating interval ( h )	24	
Minimum film temperature ( $^{\circ}\text{C}$ )	-	
Dirt pick-up class UNI EN 10792		
Resistance to washing (UNI 10560) cycles:	-	
Flashpoint ( $^{\circ}\text{C}$ )	>21	
Temperature resistance ( $^{\circ}\text{C}$ )	100	

**Notice** Data refer to the product mixed at 20  $^{\circ}\text{C}$ .

## SUPERSETA

Satin synthetic enamel for indoor/outdoor



### technical data sheet

Revision 1 fro 01/02/2017

#### STORAGE (dry and cool place)

24 months in tightly closed package, protected from frost and heat sources

#### Storage temperature (°C)

+5 ÷ +30

#### Unit size

0,75 l - 2,5 l - 20 kg

### Safety instructions

Products must be treated with attention, avoid the skin contact. Users will have to follow the actual laws. Actions as wet sanding, sanding, removal with flame, etc. of old painting coats can generate dust and dangerous smokes. Work in well aereated areas and wear the adequate individual protection means.

In Italy Decree 303 and 547 concern the rules valid for the application operations. For further information concerning the right product elimination, storage and manipulation please consult the relative technical data sheet. Data in this technical sheet are only given for information and are the result of laboratory tests and practical experience, However, the factory is not responsible if the product isn't used under its direct control.

SESTRIERE VERNICI Srl Technical Assistance is available to give all information necessary for a correct use of the product.

Be careful: the product could show, towards some subject who are particularly sensitive to isothiazolones, a little irritation. It's thus recommended to use gloves and protective glasses and to wash very well the parts which could by chance touch the skin.