



IRON MIOX

Micaceous iron polish, anticorrosive for iron surfaces with no patchy finish



technical data sheet

Revision 1 fro 01/02/2017

Converter name

-

Destination

Finish at high anticorrosie powerd given by the high micaceous iron oxyd. Suitable also in marine and iindustrial environment. Applicable on iron and steel surfaces as well as properly prepared.

Characteristics

Excellent filling
Excellent covering
Excellent weathering resistance
Excellent adhesion
Excellent brushability and relaxing

VOC (Directive 2004/42/CE) (g/l)

Monocomponent paintings at high performances.
EU limit value for this product (Cat. A/i): 500 g/l (2010). This product contains max. 500 g/l

Recommended surface and temperature conditions

Avoid applications at room temperature under +5°C or over +35°C and relative room humidity over 80%. Verify surface suitability according to humidity degree with hygrometer . Support temp: min: +5°C - max +35°C.
WARNING: areate the environment to avoid humidity accumulation
WARNING: the complete film polymerisation comes after 7-10 days at T=20°C e U.R.60%
Avoid applications with superfcial condensation or under direct sun action
In enclosed spaces, properly ventilate the area during appliacion and drying

Reccomendations

Well mix before use.
We reccomend to apply the product evenly along the whole painting surface, avoiding to leave uncovered parts from which it could start a deterioration process of the applied cycle film and the support.
At application temperatures lower than +15°C it could be necessary to add more solvent to obtain teh desired application viscosity, Too much thinner will lead to a diminution of the sagging resistsance and could bring to defects during the application.
High humidity can cause opacification dulling during the application.
We recommend the use of soft sponges with neutral detergent to clean the painted surfaces. Avoid using abrasive cloths or rags as well as alcool detergents or any type of solvent.

WARNING: for indoor application areate the environment and wear the adequate individual protection instruments

The antirust-painted surfaces must be recoated as soon as possible with finish enamels , in order too keep unchanged over time the anticorrosive power of their pigments, which could be considerably reduced for long periods outdoor



IRON MIOX

Micaceous iron polish, anticorrosive for iron surfaces with no patchy finish



technical data sheet

Revision 1 fro 01/02/2017

Application cvcle

Never painted ferrous metal surfaces

Completely remove the possible calamine and rust on the surface through sandblasting Sa 2 1/2 or manual or mechanical cleaning (brushing ST3)

WARNING: the sanded surfaces mus be recovered in 8 hours

Carefully wash to eliminate possible contamination substances

Be sure that the support is completely dry

Apply 2 coats of IRON MIOX with an interval of at least 24 hours from each other

Already painted ferrous metal surfaces

Cleaning through manual or mechanical system until complete elimination of old painting coats which are not well anchored and of possible rust spots.

Roughen the old, well anchored paintings and eliminate the sanding dust.

In case of strongly deteriorated surfaces we recommend to eliminate the old paintings and the rust caused by sand blasting Sa 2 1/2 or to remove paint and then eliminate the rust through cleaning by manual or mechanical system (brushing ST3).

WARNING: the sanded surfaces must be covered with a firts antirust coat in 8 hours

Remove the dust from the surface

Be sure that the support is completely dry.

Apply 2 coats of IRON MIOX with an interval of at least 24 hours from each other

Galvanized surfaces, aluminum and light alloys

Carefully clean the surface from possible oxides through manual or mechanical system cleaning

Otherwise, carefully clean with solution DECAPHOS and let it work for a few minutes before a careful washing for the complete removal of the phosphatizing and degreasing solution

WARNING: residual of the solution DECAPHOS on the surface can compromise the good succes of the painting cycle Be sure that the support is perfectly dry

Apply 1 coat of anticorrosive primer as our ZINCPALST 11254

After at least 12 hours apply 2 coats of IRON MIOX with an inteval of at least 24 hours from each other

PVC and ABS surfaces

Remove dust from support.

Check that the support is perfectly dry.

Apply a coat of anticorrosive primer like our ZINCPPLAST 11254 .

After at least 12 hours apply two coats of Nome Prodotto with a 24 hours interval from each other.



IRON MIOX

Micaceous iron polish, anticorrosive for iron surfaces with no patchy finish



technical data sheet

Revision 1 fro 01/02/2017

Application cvcle

New or carried forward wood surfaces

Lightly sand to remove the raised wood fibers. Remove the possible resin through adequate thinner. Fill the imperfections with synthetic stucco. sand the stuccoed parts and remove dust. Be sure that the wall is not too much wet. On high absorption woods apply a coat of 1540 LIGNOWAX to uniform the surface absorptions.

BE CAREFUL to the treatment on tannin rich woods. In order to reduce the dark spots formation, apply adequate insulating first coat

Sand the surface and then apply 1 or 2 first coat of filling first coat as our D'ECO' UNIVERSAL PRIMER or DUROPAC. After at least 12 hours apply 2 layers of IRON MIOX with an interval of at least 24 hours from each other. .

Painted wood surfaces

Sand to eliminate the wood fibers

Remove old paintings not well anchored.

Roughen the old well anchored paintings and eliminate the sanding dust

Remove the possible resin by using adequate thinner

Plaster imperfections with synthetic stucco. Sand the stuccoed parts and remove dust

Make sure that the wood isn't too much wet.

Apply 1 or 2 coats of filling primer as D'ECO UNIVERSAL PRIMER or DUROPAC

After at least 12 hours apply 2 coats of IRON MIOX with at least 24 hours interval from each other

Characteristics and technical informations

Data observable at T=20°C and 60% relative humidity

Tin aspect

Liquid. Light thixotropic.

RESIN

Alkyd

Color

Iron micaceous iron color cards

Paints achievable with MCS tintometric system

The brilliance can change depending on the paint

Use



Airbrush



Brush



Roll





IRON MIOX

Micaceous iron polish, anticorrosive for iron surfaces with no patchy finish



technical data sheet

Revision 1 fro 01/02/2017

Thinner Ecoselva or CS/3000

Tools' cleaning CS/3000

Application process

Air Spray

Thinner (% Volume)	Ecoselva or CS/3000	5 - 15
Noozle diameter	1,4 - 1,8	
Noozle pressure (Atm/Mpa)	3 - 4	

BRUSH / ROLLER

Thinner (% Volume)	Ecoselva	0 - 10
----------------------	----------	--------

TECHNICAL DATA

Mass density (kg/l)	1,48 - 1,60	
Solids content by vol. (%)	55	
Solids content by weight (%)	75	
Brookfield viscosity (cP)	-	
ASTM 4 cup viscosity (s)	-	
Brilliance (%)	15	Mat
Out of dust (minutes)	-	
Touch dry (h)	4 - 6	
Depth dry (days)	24 - 36	
recommended dry film thickness (dtf) (μm)	40 - 50	
Theoretical spreading rate (mq^2/lt)	11 - 14	
Complete polymerisation - days	7 - 10	
Recoating interval (h)	24	
Minimum film temperature ($^{\circ}\text{C}$)	-	
Dirt pick-up class UNI EN 10792	-	
Resistance to washing (UNI 10560) cycles:	-	
Flashpoint ($^{\circ}\text{C}$)	>21	
Temperature resistance ($^{\circ}\text{C}$)	150	

Notice Data refer to the product mixed at 20 $^{\circ}\text{C}$.



IRON MIOX

Micaceous iron polish, anticorrosive for iron surfaces with no patchy finish



technical data sheet

Revision 1 fro 01/02/2017

STORAGE (dry and cool place)

24 months in tightly closed package, protected from frost and heat sources

Storage temperature (°C)

+5 ÷ +30

Unit size

0,75 - 2,5 lt

Safety instructions

Products must be treated with attention, avoid the skin contact. Users will have to follow the actual laws. Actions as wet sanding, sanding, removal with flame, etc. of old painting coats can geerate dust and dangerous smokes. Work in well areated areas and wear the adequate individual protection means.

In Italy Decree 303 and 547 concern the rules valid for the application operations. For further information concerning the right product elimination, storage and manipulation please consult the relative taitechnical data sheet. Data in this technical sheet are only given for information and are the result of laboratory tets and practical experience, However, the factory is not responsible if the product isn't used under its direct control.

SESTRIERE VERNICI Srl Technical Assistance is available to give all information necessary for a correct use of the product.

Be careful: the product could show, towards some subject who are particularly sensitive to isothiazolones, a little irritation. It's thus recommended to use gloves and protective glasses and to wash very well the parts which could by chance touch the skin.